

AD-A229 548

2

OFFICE OF NAVAL RESEARCH

Grant N00014-90-J-1193

TECHNICAL REPORT No. 36

Thermoelectric Phenomena in Metals Under Large Temperature Gradients

by

A. N. Grigorenko, P. I. Nikitin, Daniel A. Jelski and Thomas F. George

Prepared for publication

in

Journal of Applied Physics (Communications)

**Departments of Chemistry and Physics
State University of New York at Buffalo
Buffalo, New York 14260**

December 1990

**DTIC
ELECTE
DEC 20 1990
S E D**

**Reproduction in whole or in part is permitted for any purpose of the
United States Government.**

**This document has been approved for public release and sale;
its distribution is unlimited.**

AD-A229 548

REPORT DOCUMENTATION PAGE

Form Approved
OMB No. 0704-0188

1a. REPORT SECURITY CLASSIFICATION Unclassified			1b. RESTRICTIVE MARKINGS		
2a. SECURITY CLASSIFICATION AUTHORITY			3. DISTRIBUTION/AVAILABILITY OF REPORT Approved for public release; distribution unlimited		
2b. DECLASSIFICATION/DOWNGRADING SCHEDULE					
4. PERFORMING ORGANIZATION REPORT NUMBER(S) UBUFALLO/DC/90/TR-36			5. MONITORING ORGANIZATION REPORT NUMBER(S)		
6a. NAME OF PERFORMING ORGANIZATION Depts. Chemistry & Physics State University of New York		6b. OFFICE SYMBOL (If applicable)	7a. NAME OF MONITORING ORGANIZATION		
6c. ADDRESS (City, State, and ZIP Code) Fronczak Hall, Amherst Campus Buffalo, New York 14260			7b. ADDRESS (City, State, and ZIP Code) Chemistry Program 800 N. Quincy Street Arlington, Virginia 22217		
8a. NAME OF FUNDING/SPONSORING ORGANIZATION Office of Naval Research		8b. OFFICE SYMBOL (If applicable)	9. PROCUREMENT INSTRUMENT IDENTIFICATION NUMBER Grant N00014-90-J-1193		
8c. ADDRESS (City, State, and ZIP Code) Chemistry Program 800 N. Quincy Street Arlington, Virginia 22217			10. SOURCE OF FUNDING NUMBERS		
			PROGRAM ELEMENT NO.	PROJECT NO.	TASK NO.
					WORK UNIT ACCESSION NO.
11. TITLE (Include Security Classification) Thermoelectric Phenomena in Metals Under Large Temperature Gradients					
12. PERSONAL AUTHOR(S) A. N. Grigorenko, P. I. Nikitin, Daniel A. Jelski and Thomas F. George					
13a. TYPE OF REPORT		13b. TIME COVERED FROM _____ TO _____		14. DATE OF REPORT (Year, Month, Day)	
				15. PAGE COUNT 9	
16. SUPPLEMENTARY NOTATION Prepared for publication in the <i>Journal of Applied Physics (Communications)</i>					
17. COSATI CODES			18. SUBJECT TERMS (Continue on reverse if necessary and identify by block number)		
FIELD	GROUP	SUB-GROUP	THERMOELECTRIC PHENOMENA NONLINEAR CONTRIBUTIONS		
			METALS PARABOLIC DISPERSION LAW		
			LARGE TEMPERATURE GRADIENTS MEASURABLE EFFECTS.		
19. ABSTRACT (Continue on reverse if necessary and identify by block number) Nonlinear contributions to thermoelectricity are studied when large temperature gradients are present in metals. A theory is presented to account for these phenomena in the case of monovalent metals obeying a parabolic dispersion law. Simple experiments are proposed in which nonlinear terms are relevant and produce measurable effects.					
20. DISTRIBUTION/AVAILABILITY OF ABSTRACT <input checked="" type="checkbox"/> UNCLASSIFIED/UNLIMITED <input checked="" type="checkbox"/> SAME AS RPT <input type="checkbox"/> DTIC USERS			21. ABSTRACT SECURITY CLASSIFICATION Unclassified		
22a. NAME OF RESPONSIBLE INDIVIDUAL Dr. David L. Nelson			22b. TELEPHONE (Include Area Code) (202) 696-4410		22c. OFFICE SYMBOL

THERMOELECTRIC PHENOMENA IN METALS UNDER LARGE TEMPERATURE GRADIENTS

A. N. Grigorenko and P. I. Nikitin
General Physics Institute, USSR Academy of Sciences
38 Vavilov Street, 117942 Moscow, USSR

Daniel A. Jelski*
Department of Chemistry
State University of New York, College at Fredonia
Fredonia, New York 14063

Thomas F. George
Departments of Chemistry and Physics & Astronomy
239 Fronczak Hall
State University of New York at Buffalo
Buffalo, New York 14260

ABSTRACT

Nonlinear contributions to thermoelectricity are studied when large temperature gradients are present in metals. A theory is presented to account for these phenomena in the case of monovalent metals obeying a parabolic dispersion law. Simple experiments are proposed in which nonlinear terms are relevant and produce measurable effects.

* Author to whom correspondence should be addressed.

Accession For	
NTIS GRA&I	<input checked="" type="checkbox"/>
DTIC TAB	<input type="checkbox"/>
Unannounced	<input type="checkbox"/>
Justification	
By	
Distribution/	
Availability Codes	
Dist	Avail and/or Special
A-1	

5
INSPECTED
COPY
DTIC

The conventional theory of thermoelectric phenomena is based on the concept of local equilibrium and small deviations from global thermal equilibrium. In this case, only linear relations between flows and thermodynamic forces should be considered, and linear nonequilibrium thermodynamics is valid. Such considerations account for the well-known Thomson and Seebeck effects, described in many textbooks.^{1,2}

However, the conventional theory of thermoelectricity excludes the so-called Benedicks' effect in metals.³ This effect is a thermoelectric phenomenon in which a potential is developed between two points at the same temperature, but separated by nonzero temperature gradients as described below. It is much smaller than the Thomson effect, in which a potential is developed between two points at different temperatures, and initial experiments demonstrating Benedicks' effect were therefore inconclusive.⁴ Similar observations for semiconductors are less ambiguous.⁵

It has been hitherto assumed that large temperature gradients cannot be produced in metals because of the high thermal diffusivity. But modern achievements in short-pulse laser generation and thin-film technology force a change in this perspective. In recent experiments⁶ high voltages were measured when a pulsed laser is used to heat a thin metal film deposited on a grating, creating temperature gradients as high as 10^6 K/cm. The complexities of these experiments are beyond the scope of this paper, but suffice it to say that Benedicks' effect is one possible explanation of the observed phenomenon. In this view, the potential is produced by nonlinear thermoelectric effects caused by differential laser heating. This possibility prompts the present work, which is the first theoretical account of nonlinear thermoelectric effects in metals.

Throughout, we assume local thermal equilibrium, without which temperature would be undefined. If we define a dimensionless parameter ω as a measure of the deviation from local equilibrium, then for the experiment just described, ω can be estimated as $\omega = \frac{\ell_0 \nabla T}{T} \approx 0.1$, where ℓ_0 is the electron free path. For simplicity, we consider metals with one parabolic conduction band, e.g., for Ag, $\ell_0 = 10^{-5}$ cm (see Ref. 7, p. 268), and for the value of $\nabla T \approx 3 \times 10^6$ K/cm, we get $\omega \approx 0.1$. Thus ω is not necessarily small, and it is no longer sufficient to consider only first-order

terms. On this scale, nonlinear terms are essential and can produce measurable experimental effects. For simplicity, we consider metals with one parabolic conduction band.

It is well known⁷ that for a bulk metal with a conductivity σ , linear non-equilibrium thermodynamics yields an electric current j as

$$j = \sigma(E_{\text{eff}} - \alpha \nabla T) \quad (1)$$

where E_{eff} is the effective electric field and α is the absolute thermoelectric coefficient. The E_{eff} can be written as

$$E_{\text{eff}} = E + \nabla(\zeta/e) \quad (2)$$

where E is the external electric field and ζ is the chemical potential. When temperature gradients are sufficiently large, then Eq. (1) is insufficient, and nonlinear terms must be taken into account:

$$j = \sigma(E_{\text{eff}} - \alpha \nabla T - \alpha_1 \nabla(\Delta T) - \alpha_2 \nabla T(\Delta T) - \alpha_3 \nabla(\nabla T)^2 - \alpha_4 (\nabla T)^3 \dots) \quad (3)$$

It should be noted that the concept of local equilibrium is still valid because otherwise a local temperature $T(x)$ is undefined. This implies that $\omega < 1$, as described in above.

Our task is to evaluate the thermoelectric coefficients α_i , for $i = 1, 2, \dots$. For this purpose, we use the conventional theory of electron transport in metals,⁸ keeping terms up to third order. Let n_k be the electron density in k -state. For a stationary state in the absence of external fields, the Boltzmann equation reduces to

$$(v_k \nabla) n_k = \frac{\partial n_k}{\partial t} \Big|_{\text{coll}} \quad (4)$$

To simply evaluate the collision term on the rhs, we use the conventional τ -approximation⁸ and neglect the effect of phonon drag, assuming that the temperature is sufficiently high. By expanding n_k in a series of temperature gradients, we obtain

$$n_k = n_k^0 + g_k^1 + g_k^2 + g_k^3 + \dots \quad (5)$$

where

$$n_k^0 = \frac{1}{\exp\left(\frac{\epsilon_k - \zeta}{T}\right) + 1} \quad (6)$$

and where ϵ_k is the electron energy in the k -state. Substituting Eq. (5) into Eq. (4) and comparing the terms of same order in both parts of the expression, we get

$$g_k^1 = -\tau(\epsilon_k)(v_k \nabla) n_k^0 \quad (7)$$

$$g_k^2 = -\tau(\epsilon_k)(v_k \nabla) g_k^1 \quad (8)$$

$$g_k^3 = -\tau(\epsilon_k)(v_k \nabla) g_k^2 \quad (9)$$

We then derive an expression for j , valid for large ω , as

$$j = e \sum_k (g_k^1 v_k + g_k^2 v_k + g_k^3 v_k) \quad (10)$$

The first term in Eq. (10) is familiar from linear thermoelectric theory,^{7,8} and yields $j = -\sigma \alpha \nabla T$. The second term vanishes because of symmetry after integrating over k -space. The third term is of interest here.

In the simplest case of a spherically-symmetric Fermi surface, the integration over k -space yields⁸

$$j^i = -e \int \frac{dS d\epsilon_k}{4\pi^3 \hbar v_k} v_k^i (\tau v_k^j \nabla_j) (\tau v_k^l \nabla_l) (\tau v_k^m \nabla_m) n_k^0 \quad (11)$$

At high temperatures, the electron free path is limited by electron-phonon scattering,⁷ and τ is inversely proportional to T . Then performing simple, but somewhat cumbersome, calculations, we obtain

$$\alpha_1/T = \alpha_2/3 = \alpha_3/3 = \frac{14\pi^2 k_b^2 \tau(\mu)^2}{5me}, \quad \alpha_4 = 0 \quad (12)$$

where $\tau(\mu)$ refers to the scattering time at the Fermi energy μ , k_b is the Boltzmann constant, and where terms to order $(k_b T/\mu)^2$ are retained.

We now evaluate Benedicks' effect in metals for the following sawtooth geometry. Suppose two points, A and B, are at a temperature T_0 , and are separated by a point C at temperature T_1 . Let the temperature gradient on the segment (AC) be twice the gradient along the segment (CB). This system may be approximated by a triangle-like temperature function, in which case the problem is analytically solvable.

As usually assumed in the stationary state, there is no current, and therefore $j = 0$. From Eq. (3) the electric field can be written as

$$E = -\nabla(\zeta/e) + \alpha \nabla T + \alpha_1 \nabla(\Delta T) + \alpha_2 \nabla T(\Delta T) + \alpha_3 \nabla(\nabla T)^2 \quad (13)$$

Then the voltage arising between points A and B is

$$V_{AB} = \int_A^B E \, dx = \int_A^B \left(\frac{d^2 \alpha_1}{2dT^2} + \frac{d}{dT} (\alpha_2 + 2\alpha_3) \right) T_x'^3 \, dx \quad (14)$$

where A and B are assumed to lie along the x-axis separated by distance Δ , and $T' = dT/dx$.

From (12) it follows that $\alpha_1 \sim 1/T$ and $\alpha_2 \sim 1/T^2$. Then

$$V_{AB} = \frac{28(\pi k_b \tau_0 T_0)^2}{5me} \int_A^B \frac{T^3}{T^3} dx \approx 40 \alpha_0 \frac{(T_1 - T_0)^3 (T_0 + T_1)}{T_1^2 T_0} \frac{\lambda_0^2}{\Lambda^2} \quad (15)$$

where the 0 subscript refers to values at T_0 , and where the evaluation of the integral depends explicitly on the geometry described above. If the gradients along (AC) and (CB) are equal, then the integral vanishes and the effect disappears. If $T_0 = 300$ K, $T_1 = 600$ K, $\Lambda = 10 \mu\text{m}$, $\lambda_0 = 10^{-5}$ cm and $\alpha_0 = 10^{-6}$ V/K, then $V_{AB} \approx 2 \mu\text{V}$. This very small potential can be measured as follows. A thin, flat metal film is irradiated by short-pulsed light with spatially modulated intensity, the modulation stretching over $N = 10^4$ periods, and each period assuming the sawtooth geometry. The modulation must be accomplished by masking, since interfering laser beams will always produce symmetric gradients, and hence no effect. Summing the voltage over 10^4 periods yields $V = NV_{AB} \approx 20$ mV, which can be easily measured by conventional stroboscopic methods.

Experiments with laser irradiation of metal gratings^{6,9} provides another interesting example where large temperature gradients arise. In these experiments, thin transition or semi-metal films are evaporated onto gratings and are illuminated by pulsed laser light. Unexpectedly high voltages of about 1 V are measured along the gratings. One possible reason for this phenomenon may be Benedicks' effect caused by a laser-induced, periodic but asymmetric temperature distribution similar to that just described and evaluated for monovalent metals.

Calculations show that for transition and semi-metals, nonlinear contributions to thermoelectricity are considerably larger because of overlapping conduction bands. In this case, an inverted conduction band may be regarded as a trap,⁷ and even linear thermoelectric coefficients are one or two orders of magnitude greater than for monovalent metals. The nonlinear terms increase because of the greater length required for inter-band transmission of electrons, in particular, because of longer transmission times from d- to s-zones for transition metals. Detailed calculations of this will be given elsewhere.

We further remark that as a consequence of Eq. (3), we can see that j_x depends not only on $\partial T / \partial x$ but also on the Laplacian. Under laser irradiation of metal gratings, in addition to the periodic gradients in the x-direction, 10^6 K/cm along

the film, high-temperature gradients arise in the z -direction. The value of such gradients can easily be estimated by $\partial T/\partial z \approx (T_1 - T_0)/\delta \approx 10^8$ K/cm, where the skin depth δ is about $0.05 \mu\text{m}$ in the present case. For such gradients, the dimensionless parameter ω assumes a value greater than 1, and we are clearly in the domain of nonequilibrium thermodynamics. Any description of electron transport in this regime will require a new physical approach. Further, in the 2-dimensional case $\nabla \times \mathbf{E}$ is not necessarily zero in Eq. (13), and for this reason, the $j = 0$ condition cannot be assumed. The cold bulk substrate will serve to complete the circuit. Thus a 2-dimensional treatment of thermoelectric phenomena is significantly more complex, and this very interesting problem will be the subject of further discussion.

In conclusion, we have calculated the nonlinear contributions to thermoelectricity arising from large temperature gradients in a monovalent metal. Such contributions play an important role in various transport processes, of which one example is Benedicks' effect. We have evaluated Benedicks' effect, forbidden in the linear theory, but which may explain interesting experimental phenomena. Practical applications could include very small and convenient sensors of laser radiation parameters.¹⁰ This theory can also be extended to double-band metals such as Ni, Ti, and Bi, where the effects could be significantly greater, and also to situations where a magnetic field is present.

Acknowledgments

TFG acknowledges support by the Office of Naval Research. Acknowledgment is made by DAJ to the donors of the Petroleum Research Fund, administered by the American Chemical Society, for partial support of this research. DAJ also acknowledges that this research was partially supported by a grant from the Research Corporation. Finally, DAJ thanks the Research Foundation of the State University of New York for an Equipment Matching Grant. All authors would like to thank the Fredonia campus, including the Department of Chemistry and, especially, Andrea Domst, for hospitality shown to the Soviet authors during their visit.

References

1. C. Kittel, Introduction to Solid State Physics, 3rd Ed. (Wiley, New York, 1966).
2. N. W. Ashcroft and N. D. Mermin, Solid State Physics (Saunders, Philadelphia, 1976).
3. C. Benedicks, Ergeb. Exakt. Naturwiss. 8, 26 (1929).
4. R. R. Heikes and R. W. Ure, Jr., Thermoelectricity: Science and Engineering (Interscience, New York, 1961), p. 311.
5. J. Tauc, Czech. J. Phys. 6, 108 (1956).
6. V. I. Konov, P. I. Nikitin, D. G. Satjukov and S. A. Uglov, Laser Surface Microprocessing, ed. by V. I. Konov, B. S. Luk'yanchuk and I. W. Boyd, Proc. Soc. Photo-Opt. Instrum. Eng., in press.
7. N. F. Mott and H. Jones, The Theory of the Properties of Metals and Alloys (Oxford, Oxford, 1956), p. 310 ff.
8. J. M. Ziman, Electrons and Phonons (Oxford, Oxford, 1960).
9. V. I. Konov, P. I. Nikitin and S. A. Uglov, (unpublished).
10. V. I. Konov, P. I. Nikitin, D. G. Satjukov and S. A. Uglov, Sensors and Actuators A 22, 498 (1990).

FY90 Abstracts Distribution List for Solid State & Surface Chemistry

Professor John Baldeschwieler
Department of Chemistry
California Inst. of Technology
Pasadena, CA 91125

Professor John Eyler
Department of Chemistry
University of Florida
Gainesville, FL 32611

Dr. Sylvia Johnson
SRI International
333 Ravenswood Avenue
Menlo Park, CA 94025

Professor Paul Barbara
Department of Chemistry
University of Minnesota
Minneapolis, MN 55455-0431

Professor James Garvey
Department of Chemistry
State University of New York
Buffalo, NY 14214

Dr. Zakya Kafafi
Code 6551
Naval Research Laboratory
Washington, DC 20375-5000

Dr. Duncan Brown
Advanced Technology Materials
520-D Danury Rd.
New Milford, CT 06776

Professor Steven George
Department of Chemistry
Stanford University
Stanford, CA 94305

Professor Larry Kesmodel
Department of Physics
Indiana University
Bloomington, IN 47403

Professor Stanley Bruckenstein
Department of Chemistry
State University of New York
Buffalo, NY 14214

Professor Tom George
Dept. of Chemistry and Physics
State University of New York
Buffalo, NY 14260

Professor Max Lagally
Dept. Metal. & Min. Engineering
University of Wisconsin
Madison, WI 53706

Professor Carolyn Cassady
Department of Chemistry
Miami University
Oxford, OH 45056

Dr. Robert Hamers
IBM T.J. Watson Research Center
P.O. Box 218
Yorktown Heights, N Y 10598

Dr. Stephen Lieberman
Code 522
Naval Ocean Systems Center
San Diego, CA 92152

Professor R.P.H. Chang
Dept. Matls. Sci. & Engineering
Northwestern University
Evanston, IL 60208

Professor Charles Harris
Department of Chemistry
University of California
Berkeley, CA 94720

Professor M.C. Lin
Department of Chemistry
Emory University
Atlanta, GA 30322

Professor Frank DiSalvo
Department of Chemistry
Cornell University
Ithaca, NY 14853

Professor John Hemminger
Department of Chemistry
University of California
Irvine, CA 92717

Professor Fred McLafferty
Department of Chemistry
Cornell University
Ithaca, NY 14853-1301

Dr. James Duncan
Federal Systems Division
Eastman Kodak Company
Rochester, NY 14650-2156

Professor Leonard Interrante
Department of Chemistry
Rensselaer Polytechnic Institute
Troy, NY 12181

Professor Horia Metiu
Department of Chemistry
University of California
Santa Barbara, CA 93106

Professor Arthur Ellis
Department of Chemistry
University of Wisconsin
Madison, WI 53706

Professor Roald Hoffmann
Department of Chemistry
Cornell University
Ithaca, NY 14853

Professor Larry Miller
Department of Chemistry
University of Minnesota
Minneapolis, MN 55455-0431

Professor Mustafa El-Sayed
Department of Chemistry
University of California
Los Angeles, CA 90024

Professor Eugene Irene
Department of Chemistry
University of North Carolina
Chapel Hill, NC 27514

Professor George Morrison
Department of Chemistry
Cornell University
Ithaca, NY 14853

Professor Daniel Neumark
Department of Chemistry
University of California
Berkeley, CA 94720

Professor Robert netten
Department of Chemistry
University of California
Los Angeles, CA 90024

Professor David Ramaker
Department of Chemistry
George Washington University
Washington, DC 20052

Professor R. Stanley Williams
Department of Chemistry
University of California
Los Angeles, CA 90024

Dr. Gary Rubloff
IBM T.J. Watson Research Center
P.O. Box 218
Yorktown Heights, NY 10598

Professor Nicholas Winograd
Department of Chemistry
Pennsylvania State University
University Park, PA 16902

Professor Richard Smalley
Department of Chemistry
Rice University
P.O. Box 1892
Houston, TX 77251

Professor Aaron Wold
Department of Chemistry
Brown University
Providence, RI 02912

Professor Gerald Stringfellow
Dept. of Matls. Sci.
& Engineering
University of Utah
Salt Lake City, UT 84112

Professor Vicki Wysocki
Department of Chemistry
Virginia Commonwealth University
Richmond, VA 23284-2006

Professor Galen Stucky
Department of Chemistry
University of California
Santa Barbara, CA 93106

Professor John Yates
Department of Chemistry
University of Pittsburg
Pittsburg, PA 15260

Professor H. Tachikawa
Department of Chemistry
Jackson State University
Jackson, MI 39217-0510

Professor William Unertl
Lab. for Surface Sci.
& Technology
University of Maine
Orono, ME 04469

Dr. Terrell Vanderah
Code 3854
Naval Weapons Center
China Lake, CA 93555

Professor John Weaver
Dept. of Chem. Eng. & Mat. Sci.
University of Minnesota
Minneapolis, MN 55455

Professor Brad Weiner
Department of Chemistry
University of Puerto Rico
Rio Piedras, Puerto Rico 00931